

Solvent-based Dye Technical Data Sheet

AmeriPolish Polished Concrete Dye System

AmeriPolish solvent-based dye is formulated using extremely fine molecules of color designed to penetrate and color any cementitious surface (All bond barriers must be removed prior to application of dye). AmeriPolish dye was created for use with polished concrete, but can be used as a base color or touch up for concrete that has received integral color, dry shake hardeners, acid stains or even as an overlay to itself. Prior to starting your project, always apply the dye to a sample area at the actual site in order to confirm that the floor is receptive to the dye, and to establish the desired color. The addition of the [EnhancerPro™ Series Penetrating Agent](#) is an integral component of the AmeriPolish System.

REMEMBER that dyes will not mask or hide imperfections in the floor, and may appear different in areas that have received different pours or patches.

1. Explanation: Ameripolish solvent-based dye is packaged in powder form to be mixed with acetone by the customer. AmeriPolish dye is offered in 23 standard colors. Custom colors are available for an additional fee and minimum order. Be aware that paint colors that contain a white base cannot be replicated. Dye colors can be combined to create an unlimited number of color variations. When applied properly AmeriPolish dye gives great color to polished concrete floors or it can produce a look similar to an acid stain with a sealer. Anytime that AmeriPolish dye is used on a process other than polished concrete a sealer is required. This brightens the color and retards color fading over time. The [AmeriPolish ProGuard™ Stain Shield](#), an impregnating sealer, should be applied to provide added protection against oil and water-based spills and stains. Concrete, even after becoming densified and polished, is still a porous substrate, and all densifiers require 2-6 months to attain full densification.

2. Benefits:

- Large selection of vibrant colors
- Extremely easy to apply
- Can be applied to any cementitious surface
- Packaged in dry form for easy shipping and storage
- Unlimited shelf life in powder form.

3. Mixing: Ameripolish dye is packaged in powder form in 1 quart, 1 gallon or 5 gallon increments and needs to be mixed with a corresponding amount of acetone. Empty the dye into the container of acetone and shake vigorously for approximately 30 seconds. Let the container set for 3 hours before use. The [EnhancerPro™ Series Penetrating Agent](#) should be added to the mixed dye in all instances, EXCEPT when coloring very porous concrete, or applying dye around stencils where the acetone could cause adhesive release and dye bleed. The [Penetrating Agent](#) slows down the “flashing” of the acetone, allowing better dye penetration in tight, densified concrete, and in hot weather. Immediately before application shake again for approximately 30 seconds. This will ensure that all the dye has mixed with the acetone. Wear protective gloves and safety glasses when mixing.

4. Application: **SURFACES MUST BE CLEAN AND DRY BEFORE APPLICATION OF THE DYE.** Protect all adjacent surfaces that are not specified to receive the dye, as the dye will also penetrate adjacent concrete, masonry or wood finishes. Use masking materials that will not be affected by the acetone in order to keep the dye from bleeding between surfaces. The dye is best applied with the [Patriot SpraySafe™ System's](#) CO2 sprayers (www.patriotsprayer.com). It is recommended that only a conical tip be used, as a fan tip can leave a linear pattern from the dye application. A consistent spray coverage and pattern are best achieved when using a pre-set ceramic insert conical tip and constant pressure. Maintain a container or bucket in the application area to store the tip and wand in between applications. In order to achieve the maximum life of your sprayer, immediately upon completion of your dye application, run clear acetone through the pump and wand, followed by clean water. This is recommended between color changes, and prior to storing the sprayer between jobs. **CAUTION: TAKE CARE IN MIXING, TRANSPORTING AND APPLYING THE MIXED DYES AS DRIPS OR SPILLS CAN BECOME PERMANENT.** The dye particles are susceptible to air movement-protect all surfaces or equipment from dye drift.

5. Polished Concrete: Always apply dye in a small test area to confirm color acceptance on your project slab. For projects involving a densifier we recommend the following sequencing of dye application. (Remember: if you do not apply a densifier you will need to protect the dye with a topical sealer) Establish your grinding level starting point, then grind the floor up through the 400 grit level prior to dye application. Apply the dye in a consistent, overlapping circular motion, holding the wand approximately 12 inches above the surface. Following the initial dye application, wait 1-2 minutes and wipe an area with a dry white cloth to establish color acceptability. Should your project require an additional dye application to achieve the desired color, you may apply the second application once the first application is completely dry. Multiple light applications are recommended, instead of one heavy one. The floor will only accept a set amount of dye

per application, and the excess will remain as residue that must be removed.

6. Cleaning: Following your last dye application, it is mandatory that you clean the floor with water and a soft brush or pad. During your initial cleanings expect a small amount of residual dye to release from the concrete, as residual dye that did not penetrate the concrete will remain on the surface of the concrete. Clean the floor until the rinse water is clear, vacuuming up all rinse water. As you become more experienced with the dye application, and how much is required for a particular floor, the amount of residue will be less. **You may now proceed with the application of your densifier and final polishing steps. Follow the application instructions of your densifier manufacturer.**

7. Coverage Rates: Ameripolish coverage rates will vary significantly from floor to floor based on the roughness of the concrete, the porosity and the mix design. Expect approximately 400 square feet per gallon for your first application, and 500-600 square feet for each additional application.. Sprayer and tip design can lead to wasted dye and an inconsistent appearance. Dye is being sprayed too heavily if puddles are present.

8. OPTIONAL-Additional Dye Application: For further enhancement of your dye color, you may apply an additional application of dye following the completion of your polishing steps. Apply and clean the dye according to the information in steps 5 and 6, then once the floor is dry, proceed to step 9.

9. Impregnator Application: ProGuard™ Stain Shield was formulated for compatibility with the dyes, and is recommended for protection of all dyed concrete; especially in areas that will be exposed to foods or oils to provide additional water and oil-stain resistance.

10. OPTIONAL- Crystallization: Crystallization may be utilized to further enhance the colors and protection of the floor. It is recommended that you use either a high-speed burnisher with a Gorilla Lite pad, or a 175-rpm floor machine with steel wool. Apply following the application of the ProGuard™ Stain Shield.

11. Floor Protection: If the floor work is not the last step to be performed prior to project turnover, then protect the floor following completion of your scope of work with a breathable covering such as kraft paper.

12. Safety precautions: WARNING – Before using or handling this material, read the Material Safety Data Sheet and Warranty. AmeriPolish concrete dyes are highly flammable when mixed with acetone. Great care should be taken when using this product! Acetone will produce vapors that are highly flammable and can be harmful to the applicator's health. Make sure rooms are properly ventilated. Open windows and use fans to achieve air movement. Non-explosive exhaust devices may be required in areas with poor ventilation. Make absolutely certain no source of open flame is present. Pilot lights, heaters, cigarettes, and electric tools should not be used or turned on until all vapors have dissipated. Always wear a carbon filter respirator, eye protection, and chemical resistant gloves. Devices are available to measure acetone vapors. KEEP OUT OF REACH OF CHILDREN. DO NOT TAKE INTERNALLY.

13. Warranty: This product is manufactured only for use by trained and licensed contractors and installers who have been trained in the proper use of the material. The manufacturer guarantees that the product will be of consistent color and mixture when received. The manufacturer has no control over the use of this product; therefore, no warranty, expressed or implied, is or can be made to either the effects or results of such use. In any case, the sellers and manufacturer's obligation under this warranty shall be limited to refunding the purchase price or replacing material proven defective.

14. Health Cautions: AmeriPolish decorative concrete dye is highly flammable when mixed with acetone. Always provide plenty of ventilation when applying the dye. Vapors may cause flash fires. No open flames may be present. Electrical tools, pilot lights, heaters, and cigarettes should not be used if fumes are present. Devices are available to measure acetone vapors.

* It is important to note, that as of 2/01/06 the United States Environmental Protection Agency's June 16, 1995 volatile organic compounds (VOC) classification for acetone remains in effect. The EPA has granted acetone VOC-exempt status. In addition, acetone is not a hazardous air pollutant (HAP) under the Clean Air Act Amendment of 1990. Most states, such as California, follow these federal guidelines. Please check with your individual state if the question arises.